

# SC-423S

Ferritic STS Type

## Conformances


## Applications

- Continuous casting rolls, steel mill rolls

## Features

- Submerged arc type hardfacing wire(build-up)
- Ferritic stainless steel type

## Welding Position



## Current

DC +

## Welding Process

SAW(with S-717/S-401HF flux)

## Diameter / Packaging

Diameter	Coil		Pac	
	25kg (55lbs)	150kg (330lbs)	250kg (551lbs)	
mm (in)				
3.2 (1/8)	✓	✓	✓	

## Typical Chemical Composition of All-Weld Metal (%)

	C	Si	Mn	Cr	Ni	Mo	Nb	V
As welded with 3.2mm wire	0.06	0.4	1.4	17.0	2.4	1.1	0.2	0.3

## Typical Mechanical Properties of All-Weld Metal

	Rockwell Hardness(HRc) (≥3layers)
On Mild Steel (3.2mm)	5-10

## Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
3.2mm (1/8in), DC+					
Submerged Arc	25 (1)	1.4 (55)	350	28	3.7 (8.1)
		1.7 (66)	390	30	4.4 (9.7)
		1.8 (72)	430	31	5.2 (11.4)

SMAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX