

SC-430S

Ferritic STS Type

Conformances


Applications

- Continuous casting rolls, steel mill rolls

Features

- Submerged arc type hardfacing wire(build-up)
- Ferritic stainless steel type

Welding Position



Current

DC +

Welding Process

SAW(with S-717/S-401HF flux)

Diameter / Packaging

Diameter	Coil	Pac	
mm (in)	25kg (55lbs)	150kg (330lbs)	250kg (551lbs)
3.2 (1/8)	✓	✓	✓

Typical Chemical Composition of All-Weld Metal (%)

	C	Si	Mn	Cr
As welded with 2.4/3.2mm wire	0.05	0.7	1.3	17.0

Typical Mechanical Properties of All-Weld Metal

	Rockwell Hardness(HRc) (≥3layers)
On Mild Steel (2.4/3.2mm)	5~10

Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
3.2mm (1/8in), DC+					
Submerged Arc	25 (1)	1.4 (55)	350	28	3.8 (8.4)
		1.7 (66)	390	30	4.5 (9.9)
		1.8 (72)	430	31	5.3 (11.6)