

## SM-CuNi10

Type: Copper Nickel

As the usage of copper wire in welding field is increasing; **HYUNDAI WELDING** is geared to offer a rapid response to clients' specific requirements. With constant research and development, our range of Copper wire will continue to evolve to offer the global market new grades and products that covers a multitude of applications.

### Conformances

AWS A5.7  
EN ISO 14640 **CuNi10**  
GB/T9460 **SCu7061**

### Shielding Gas

Argon 100%

### Key Features

- Especially good for seawater corrosion resistance
- Particularly suitable for the welding and hard facing Copper nickel alloys and welding of non-ferrous alloys, Dissimilar steel materials

### Typical Application

- Machinery
- Desalting of seawater
- Ship-Building
- Oil refinery
- Food processing industries

### Chemical Composition (%)

Cu	Fe	Mn	Ni	P	Pb	Si	C	Ti	S	Others
bal.	0.5-2.0	0.5-1.5	9.0-11.0	0.02	0.02	0.2	0.05	0.01-0.5	0.02	0.4

### Mechanical Properties

Tensile Strength (Rm)	Elongation
300 N/mm <sup>2</sup>	34 %



# SM-CuNi10

GB/T9460 SCu 7061  
EN ISO 14640 - CuNi10

Type: Copper Nickel

## Applicable Joining Processes

Applicable Joining Processes										
Alloy	UNS No.	Oxyfuel Gas Welding	SMAW	GMAW	GTAW	Resistance Welding	Solid-state Welding	Brazing	Soldering	Electron Beam Welding
ETP Copper	C11000-C11900	NR	NR	F	F	NR	G	E	G	NR
Oxygen-Free Copper	C102000	F	NR	G	G	NR	E	E	E	G
Deoxidized Copper	C12000-C123000	G	NR	E	E	NR	E	E	E	G
Beryllium-Copper	C17000-17500	NR	F	G	G	F	F	G	G	F
Cadmium/Chromium Copper	C16200-C18200	NR	NR	G	G	NR	F	G	G	F
Red Brass – 85%	C23000	F	NR	G	G	F	G	E	E	-
Low Brass – 80%	C24000	F	NR	G	G	G	G	E	E	-
Cartridge Brass – 70%	C26000	F	NR	F	F	G	G	E	E	-
Leaded Brasses	C31400-C38590	NR	NR	NR	NR	NR	NR	E	G	-
Phosphor Bronzes	C50100-C52400	F	F	G	G	G	G	E	E	-
Copper Nickel 30%	C71500	F	F	G	G	G	G	E	E	F
Copper Nickel 10%	C70600	F	G	E	E	G	G	E	E	G
Nickel Silvers	C75200	G	NR	G	G	G	G	E	E	-
Aluminum Bronze	C61300 C61400	NR	G	E	E	G	G	F	NR	G
Silicon Bronzes	C65100 C65500	G	F	E	E	G	G	E	G	G

E=Excellent    G=Good    F=Fair    NR =Not Recommended

| Courtesy of American Welding Society Welding Handbook 8

th Ed. Vol. 3 Part 1

## Recommended Welding Amperage

GMAW (DCRP) Gas: 100% Ar or 75/25 Ar/He			GTAW (DCSP, ACHF) Gas : 100% Ar or He		
Diameter	Voltage	Amperes*	Diameter	Amperes* (DCEN)	Amperes* (ACHF)
.035"	20-26	100-200	1/16"	70-120	70-150
.045"	22-28	100-250	3/32"	120-160	140-230
5/32"	29-32	250-400	1/8"	170-230	225-320
3/16"	32-34	350-500	5/32"	220-280	175-300
			3/16"	280-330	200-320

\*Use low range for iron - or nickel -based alloys; middle range for bronze alloys; high range for copper

# SM-CuNi10

Type: Copper Nickel

GB/T9460 SCu 7061  
EN ISO 14640 - CuNi10

## Suggested Filler Metal Selection

Suggested Filler Metal Selections for Copper-based Alloy									
	Copper	Phosphor Bronze	Silicon Bronze	Yellow (Naval) Brass	Manganese Bronze	Navy G	Red Brass	Copper Nickel	Nickel Al Bronze
Copper	Deox (538)								
Phosphor Bronze	PHB, Deox (538)	PHB, Deox (204)							
Silicon Bronze	PHB, Deox (538)	PHB, SB (66)	SB (66)						
Yellow (Naval) Brass	SB, PHB, Deox (538)	PHB (316)	AIB-A2, SB (66)	AIB-A2 (316)					
Manganese Bronze	PHB, Deox (538)	AIB-A2, PHB (204)	AIB-A2, SB (66)	AIB-A2, PHB (316)	AIB-A2, PHB, Ni Bronze (149)				
Navy G	PHB, Deox (538)	PHB (204)	AIB-A2, SB (66)	PHB (316)	AIB-A2, PHB (316)	AIB-A2, PHB (316)			
Red Brass	PHB, Deox (538)	PHB (260)	AIB-A2, SB (66)	PHB (316)	AIB-A2, PHB (316)	AIB-A2, PHB (316)	AIB-A2, PHB (204)		
Copper Nickel	AIB-A2, Deox (538)	PHB, AIB-A2 (204)	AIB-A2 (66)	AIB-A2 (66)	AIB-A2 (149)	AIB-A2 (66)	AIB-A2 (66)	CuNi67 ERCuNi	
Nickel Aluminum Bronze	AIB-A2, Deox CuNiAl (538)	PHB (204)	AIB-A2 (66)	AIB-A2, CuNiAl (260)	AIB-A2 (149)	AIB-A2 (260)	AIB-A2 (316)	AIB-A2 (316)	CuNiAl (149)
Low Alloy Steel	AIB-A2 (538)	PHB, AIB-A2 (204)	AIB-A2 (204)	AIB-A2 (316)	AIB-A2 (204)	AIB-A2, PHB (260)	AIB-A2 (316)	AIB-A2 (204)	AIB-A2 (204)
Low Carbon Steel	AIB-A2 (538)	PHB, AIB-A2 (204)	AIB-A2 (66)	AIB-A2 (260)	AIB-A2 (66)	AIB-A2, PHB (316)	PHB (316)	AIB-A2 (66)	AIB-A2 (149)
Medium Carbon Steel	AIB-A2 (538)	PHB, AIB-A2 (204)	AIB-A2 (66)	AIB-A2 (260)	AIB-A2 (204)	AIB-A2, PHB (316)	AIB-A2 (316)	AIB-A2 (204)	AIB-A2 (204)
High Carbon Steel	AIB-A2 (538)	PHB, AIB-A2 (260)	AIB-A2 (204)	AIB-A2 (260)	AIB-A2 (260)	AIB-A2, PHB (316)	AIB-A2 (316)	AIB-A2 (260)	AIB-A2 (260)
Cast Iron	AIB-A2 (538)	PHB, AIB-A2 (204)	AIB-A2, SB (149)	AIB-A2 (316)	AIB-A2 (204)	AIB-A2, PHB (316)	AIB-A2, PHB (316)	AIB-A2 (204)	AIB-A2 (204)

Temperature in parentheses is the recommended preheat and interpass (Celsius) temperature.

Recommended Tungsten Electrodes for GTAW are 2% Thoriated , 2% Ceriated , 2% Lanthanum or E3 (EWG).

Notes: PHB = Phosphor Bronze  
Deox = Deoxidized Copper  
SB = Silicon Bronze  
AIB - A2 = Aluminium Bronze A -2  
CuNiAl = Copper Nickel Aluminum Bronze  
CuNi67 = Copper Nickel 67

## Standard Packaging

Packaging				
Packaging Type	Image	Diameter	Weight	Remark
Rods		1.2 ~ 9.5 mm		Length: 350 ~ 1000 mm  Rod identification possible by stamping. Color for flux coated TIG rods: white, blue, yellow
Spool		0.6 ~ 1.6 mm	1 ~ 15 kg	Type: D100, D200, D300, K300, BS300
Wood		0.8 ~ 2.4 mm	Max. 250 kg	
Drums		0.8 ~ 1.6 mm	100 ~ 250 kg	
Coils		1.6 ~ 6.0 mm	15 ~ 100 kg	Outer $\theta$ : 450 ~ 650 mm  Inner $\theta$ : 250 ~ 450 mm