

# SMT-2594

25%Cr-7%Ni-4.5%Mo-0.25%N Super Duplex STS

## Conformances

AWS A5.9/ ASME SFA5.9 ER2594  
 EN ISO 14343-A G 25 9 4 NL  
 ABS AWS A5.9 ER2594  
 LR AWS A5.9 ER2594  
 DNV-GL Duplex Stainless Steels (-50°C)


## Applications

- Offshore structure & FPSO, chemical and petrochemical plants

## Features

- Excellent corrosion resistance
- Superior pitting resistance

## Welding Position



## Current

GMAW: DC + / GTAW: DC -

## Shielding Gas

Ar / Ar+ O<sub>2</sub>

## Diameter / Packaging

| Diameter    | Spool          |               |              | Pac            |                |                |
|-------------|----------------|---------------|--------------|----------------|----------------|----------------|
|             | 12.5kg (28lbs) | 15kg (33 lbs) | 20kg (44lbs) | 150kg (330lbs) | 200kg (440lbs) | 250kg (551lbs) |
| 0.8 (0.033) | ✓              |               |              |                |                |                |
| 0.9 (0.035) | ✓              |               |              |                |                |                |
| 1.0 (0.040) | ✓              |               |              |                |                |                |
| 1.2 (0.045) | ✓              |               |              |                |                |                |
| 1.4 (0.052) |                |               |              |                |                |                |
| 1.6 (1/16)  | ✓              |               |              |                |                |                |

| Diameter | 5kg*1000    |             |            |            |            |            |           |
|----------|-------------|-------------|------------|------------|------------|------------|-----------|
|          | 1.0 (0.039) | 1.2 (0.045) | 1.6 (1/16) | 2.0 (5/64) | 2.4 (3/32) | 2.6 (0.10) | 3.2 (1/8) |
|          |             |             | ✓          | ✓          | ✓          | ✓          | ✓         |

SMAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX

### Typical Chemical Composition of the Wire(%)

| C     | Si   | Mn   | P     | S     | Cr    | Ni   | Mo   | Cu   | N     |
|-------|------|------|-------|-------|-------|------|------|------|-------|
| 0.011 | 0.41 | 0.53 | 0.019 | 0.001 | 25.27 | 9.13 | 3.86 | 0.21 | 0.257 |

### Typical Mechanical Properties of All-Weld Metal

| TS<br>MPa(lbs/in <sup>2</sup> ) | EL<br>(%) | Temp<br>°C(°F) | CVN-Impact Value<br>J (ft·lbs) | PREN |
|---------------------------------|-----------|----------------|--------------------------------|------|
| 890 (129,000)                   | 28.6      | -50 (-58)      | 195 (144)                      | 40   |

### Typical Welding Parameters

| Diameter, Polarity<br>Shielding Gas | CTWD<br>mm(in)       | Wire Feed Speed<br>m/min (in/min) | Amp.<br>(A) | Volt.<br>(V) | Deposition Rate<br>kg/hr (lb/hr) |
|-------------------------------------|----------------------|-----------------------------------|-------------|--------------|----------------------------------|
| <b>1.0mm (0.040 in), DC +</b>       |                      |                                   |             |              |                                  |
| 100% Ar Gas                         | 15~20<br>(0.59~0.78) | 6.0 (236)                         | 140         | 24           | 2.1 (4.6)                        |
|                                     |                      | 7.1 (280)                         | 160         | 24           | 2.5 (5.5)                        |
|                                     |                      | 9.2 (362)                         | 190         | 24           | 3.2 (7.1)                        |
| Mixed Gas (Ar + 2% O <sub>2</sub> ) | 15~20<br>(0.59~0.78) | 5.2 (204)                         | 160         | 26           | 1.8 (4.0)                        |
|                                     |                      | 7.0 (276)                         | 190         | 26           | 2.4 (5.3)                        |
|                                     |                      | 8.3 (327)                         | 220         | 26           | 2.9 (6.4)                        |
| <b>1.2mm (0.045 in), DC +</b>       |                      |                                   |             |              |                                  |
| 100% Ar Gas                         | 15~20<br>(0.59~0.78) | 9.2 (362)                         | 190         | 27           | 4.6 (10.1)                       |
|                                     |                      | 11.9 (469)                        | 220         | 27           | 6.0 (13.2)                       |
|                                     |                      | 15.5 (610)                        | 260         | 27           | 7.8 (17.2)                       |
| Mixed Gas (Ar + 2% O <sub>2</sub> ) | 15~20<br>(0.59~0.78) | 7.7 (303)                         | 200         | 28           | 3.9 (8.6)                        |
|                                     |                      | 8.6 (339)                         | 230         | 28           | 4.3 (9.5)                        |
|                                     |                      | 10.1 (398)                        | 260         | 28           | 5.1 (11.2)                       |