

# ST-309L

22%Cr-12%Ni steel, 18%Cr-8%Ni clad steel, STS-CrMo, STS-Carbon steel



## Conformances

AWS A5.9/ ASME SFA5.9 ER309L  
 JIS Z3321 YS309L  
 EN ISO 14343-A W 23 12L  
 ABS AWS A5.9 ER309L  
 LR SS/CMn  
 BV 309L  
 DNV-GL VL 309L  
 NK KY309L  
 CCS 309L  
 CE

## Applications

- Steel Structures - Oil, Textile industries, Nuclear reactor

## Features

- Resistance to crack
- High efficiency
- Excellent resistance to heat

## Current

DC -

## Shielding Gas

Ar

## Diameter / Packaging

Diameter	
mm (in)	5kg*1000
1.0 (0.039)	
1.2 (0.045)	√
1.6 (1/16)	√
2.0 (5/64)	√
2.4 (3/32)	√
2.6 (0.10)	√
3.2 (1/8)	√

## Typical Chemical Composition of the Wire(%)

C	Si	Mn	Cr	Ni
0.03	0.40	1.74	24.2	12.6

## Typical Mechanical Properties of All-Weld Metal

TS MPa(lbs/in <sup>2</sup> )	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft-lbs)
600 (87,000)	38	0 (32)	150 (110)