

# ST-309MoL

Dissimilar metals such as stainless steels and carbon steels

## Conformances

AWS A5.9/ ASME SFA5.9 ER309LMo  
JIS Z3321 YS309LMo  
EN ISO 14343-A W 23 12 2L  
BV SA309Mo

## Current

DC -

## Shielding Gas

Ar

## Applications

- Clad steel side welding of 316, 316L STS clad steel

## Diameter / Packaging

Diameter	
mm (in)	5kg*1000
1.0 (0.039)	
1.2 (0.045)	
1.6 (1/16)	✓
2.0 (5/64)	✓
2.4 (3/32)	✓
2.6 (0.10)	✓
3.2 (1/8)	✓

## Features

- Excellent corrosion resistance
- Excellent resistance to heat
- Excellent Arc stability and bead wetting

## Typical Chemical Composition of the Wire(%)

C	Si	Mn	Cr	Ni	Mo
0.02	0.35	1.8	23.2	13.7	2.5

## Typical Mechanical Properties of All-Weld Metal

TS MPa(lbs/in <sup>2</sup> )	EL (%)
650 (94,200)	32

SMAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX