

S-308Mo.16

Type : Rutile

Conformances

AWS A5.4/ ASME SFA5.4 E308Mo-16

JIS Z3221 ES308Mo-16

EN ISO 3581-A-E 20 10 3


Applications

- Stainless steel (ASTM CF8M)

Features

- Easy to remove slag
- Smooth welding
- Low spatter

Welding Position



Current

AC or DC ±

Redrying Conditions

350°C (662°F) X 1hr

Diameter / Packaging

Diameter	Length	P.V.C	
		packet	carton
mm (in)	mm (in)	2.5kg(5.5lbs)	10kg(22lbs)
2.6 (3/32)	350 (14)	✓	
3.2 (1/8)	350 (14)	✓	
4.0 (5/32)	400 (16)	✓	
5.0 (3/16)	400 (16)	✓	
6.0 (15/64)	450 (18)	✓	

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	P	S	Cr	Ni	Mo
0.03	0.65	0.77	0.032	0.017	18.5	9.7	2.3

Typical Mechanical Properties of All-Weld Metal

TS	EL
MPa(lbs/in ²)	(%)
621 (90,200)	42.3

Typical Welding Parameters / Amp.(A)

Diameter mm (in)	2.0 (5/64)	2.6 (3/32)	3.2 (1/8)	4.0 (5/32)	5.0 (3/16)
Length mm (in)	300 (12)	300 (12)	350 (14)	350 (14)	350 (14)
F & HF	25-55	50-85	70-115	95-145	135-180
V-up, OH	20-50	45-80	65-110	85-135	-

SWAW

SAW

GMWAW

GTAW

FCAW

Non-FERROUS

APPENDIX