

# Supershield CrCH

Cr-Carbide Type

## Conformances


## Applications

- Wear plate, conveyor screws, bucket teeth

## Features

- Open arc type hardfacing wire
- Cr-Carbide type

## Welding Position



## Current

DC +

## Welding Process

Open Arc

## Diameter / Packaging

Diameter	Coil		Pac
mm (in)	25kg (55lbs)	150kg (330lbs)	250kg (551lbs)
2.8 (7/64)	✓	✓	✓

## Typical Chemical Composition of All-Weld Metal (%)

	C	Si	Mn	P	S	Cr
As welded with 2.8mm wires	5.0	0.9	0.2	0.010	0.007	28.0

## Typical Mechanical Properties of All-Weld Metal

	Rockwell Hardness(HRC)		
	1 Layer	2 Layers	4 Layers
On Mild Steel (2.8mm)	53-56	56-59	59-63

## Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
<b>2.8mm (7/64in), DC+</b>					
Open Arc	25 (1)	2.9 (117)	330	28	5.2 (11.4)
		3.7 (146)	380	29	6.4 (14.1)
		4.4 (174)	430	30	7.2 (15.8)

SMW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX